



Rayher.

JUST CREATE

CRAFTING IDEA

GB

Black side plate
out of creative-cement

WWW.RAYHER.COM



Used items:

36 033 000	Casting mould Circle, 25 cm ø	1 piece
36 034 000	Casting mould Circle, 18.5 cm ø"	1 piece
34 153 000	Creative-cement	ca. 1500 g
38 000 576	DecoArt All purpose paint, black	30 ml

Additionally you need:

89 530 00	Sandpaper
37 103 00	Brush

Cooking oil, sieve, pebbles to weigh down the casting mould, support out of Crepla or cardboard

Instructions:

1 To start the preparation, put the large casting mould "Circle" on a solid and even surface, so that it doesn't wobble and coat its inside with cooking oil. Coat well the outer side of the small one too with cooking oil.

2 In order to remove the larger pebbles from the cement, you should sieve the cement powder (about 1430 g) before mixing with water, through an ordinary household sieve.

3 Pour about 150 ml of water (once the cement is sieved, the mixing ratio is changing according to the instructions on the package) and 30ml of the black acrylic paint in a plastic bucket and then gradually add approx. 1 kg of the creative-cement powder. Stir this mixture with a wooden spatula until an uniform and castable compound is obtained.

4 Fill the prepared large circle-shaped casting mould with the casting compound up (pour not quite up to the top). Allow the compound to rest for about 1-2 minutes. Tip: to reduce the air bubbles in the cement-casting compound, at first put one side of the smaller circle-shaped casting mould on the casting compound and then put the rest of the mould slowly with a slight pressure. Once the whole casting mould has been placed, you can push it with a slight pressure to the desired depth and carefully align it back and forth. After that, weigh down the casting mould to desired depth with pebbles or small stones.



5 Let it dry out overnight.

6 The next day, you can demould a part of the object. Firstly, demould carefully the smaller circle-shaped casting mould by bending and pulling it upwards slightly from all sides. Once the smaller circle-shaped casting mould has been entirely removed from the casting object, let it dry once more for a few hours.

7 Then you can demould the rest of the casting object from the mould by upturning the casting mould on the support out of Crepla or cardboard and then carefully press slightly with the palm of the hand on the casting object, so that the air penetrates between the casting object and mould. Tap the casting mould gently on your support, so that the side plate out of cement becomes entirely detached from the mould.

8 Small burrs and irregularities can be quickly & easily grinded with sandpaper.

9 The concrete side plate is not food-safe, so do not bring it into direct contact with food.

Rayher.

WWW.RAYHER.COM

© 2016, Rayher Hobby GmbH

You will find material specifications and instructions on our homepage.